

# Acrydur™ 800 BD PUMMA coating for bridge deck overlays

Fast and seamless installation on steel and concrete bridges in two layers. Curing also at low temperatures, 2 h later drivable



## Sealer

Acrydur™ 528  
100 ft<sup>2</sup>/gal  
clear

## Coating

Acrydur™ 800  
15 ft<sup>2</sup>/gal  
1:1 with s/IPET filler\*  
7,5 kg/m<sup>2</sup>  
flint

## Membrane

Acrydur™ 800  
30 ft<sup>2</sup>/gal  
1:0,5 with s/IPET filler\*  
broadcast with  
Quartz 16-30 mesh

## Primer

Acrydur™ 112/113  
75 – 100 ft<sup>2</sup>/gal  
slightly broadcast  
Quartz 0,6 – 1,2 mm

(\* ) by volume